



DECLARATION OF PERFORMANCE

DOP n° 140430400FABONEETA 2021-01-01

FOAMGLAS®FAB ONE PSH
ETA "Penetration seals"



1. Unique identification code of the product-type	FOAMGLAS®FAB ONE PSH DOP n° 140430400A 2019/01/01-ThBeli- CG-EN14305-ST(+)430-ST(-)(-265)-WS-CL2-Mu
2. Identification of the construction product as required under Art. 11(4)	Cellular glass - Fabricating ONE- PSH - "Penetration seals"
3. Intended use or uses of the construction product	Thermal insulation for industrial installations & Building Equipment "Penetration seals"
4. Name and contact address of the manufacturer as required pursuant Art. 11(5)	PCE-Pittsburgh Corning Europe NV/SA - Albertkade 1 - B3980 Tessenderlo (B) www.foamglas.com quality-compliance@foamglas.com
5. Name of the authorised representative whose mandate covers the tasks specified in Art. 12(2)	None
6. System or systems AVCP as set out in Annex V	AVCP system 1 (=> cf. certificate of constancy of performance n° 2812-CPR-JA5106)
7. Harmonised specification	ETA 20-1194
Notified body	Thermal conductivity - BBRI (No. 1136) & FIW (No. 751) / Fire reaction - WFGRT (No. 1173) / Compressive strength - BBRI (No. 1136) - Element (n° 2812)

Essential characteristics	Performance according to	Technical specification
Reaction to fire	ETA 20-1194	ETAG 26-02 (Used as EAD)
Resistance to fire		
Dangerous substances		

8. Table 1

Essential characteristics	Performance	
Thermal resistance	Thermal conductivity (λ D-value)	λ D-value see table 2
	Thickness	following order
Reaction to fire Euroclass characteristics	Reaction to fire	Euroclass A1
Durability of thermal resistance against heat, weathering, ageing/degradation	Thermal conductivity (λ D-value)	λ D-value see table 2
	Durability characteristics	Thermal conductivity of cellular glass products does not change with time, experience has shown
	Dimensional Stability	DS (70/90)
Durability of reaction to fire against heat, weathering, ageing/degradation	Durability characteristics	The fire performance of cellular glass does not deteriorate with time.
	Dimensional Stability	DS (70/90)
Tensile/flexural strength	Tensile strength parallel to faces	NPD
Durability of compressive strength against aging degradation	Compressive creep	-
Water permeability	Water absorption (short)	WS
	Water absorption (long)	WL(P)
Water vapour permeability	Water vapour resistance	∞ infinite
Acoustic absorption index	Sound absorption	AP1→NPD
Release of dangerous substances to the indoor environment	Release of dangerous substances	NPD
Min / Max Temperature range	Min / Max Temperature range	-265°C / +430°C
Trace quantities of water soluble chloride	Trace quantities of water soluble chloride	≤ 2 mg/kg
pH	pH	8-10
Continuous glowing combustion	Continuous glowing combustion	no glowing combustion

EN 14305: 2009 + A1:2013

Table 2

Thermal conductivity -180°C	λ D ≤ 0.021 W/(m•K)
Thermal conductivity -150°C	λ D ≤ 0.024 W/(m•K)
Thermal conductivity -120°C	λ D ≤ 0.027 W/(m•K)
Thermal conductivity -80°C	λ D ≤ 0.031 W/(m•K)
Thermal conductivity -40°C	λ D ≤ 0.037 W/(m•K)
Thermal conductivity 0°C	λ D ≤ 0.043 W/(m•K)
Thermal conductivity +40°C	λ D ≤ 0.050 W/(m•K)
Thermal conductivity +80°C	λ D ≤ 0.057 W/(m•K)
Thermal conductivity +120°C	λ D ≤ 0.066 W/(m•K)
Thermal conductivity +180°C	λ D ≤ 0.080 W/(m•K)
Thermal conductivity +240°C	λ D ≤ 0.096 W/(m•K)
Thermal conductivity +300°C	λ D ≤ 0.114 W/(m•K)

9. The performance of the product is in conformity with the declared performance. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer

Piet Vitse, European Director Norms & Standards, Product & Systems Certifications, Policy and Advocacy

Tessenderlo (B), 01.01.2021

Previous version: 10.07.2019